



HYDRAPHTAL 8055

Lightfast, elektrolyte-stable fatliquor

Base: combination of high-viscous animal fats with protein condensates

Appearance: white paste

Fat content: 30 %

Electric charge: anionic

Stability: against acids, salts and chrome salts in usual concentrations

APPLICATION:

Field of application:

When used in the pickle and chrome tannage, HYDRAPHTAL 8055 obtains a considerable increase of the tear- and started-tear strength.

As a pre-fatliquoring agent on softy articles, HYDRAPHTAL 8055 improves the softness and the through-fattening.

QUANTITIES TO USE:

pickle and chrome tannage: 0,5 - 2,0 % HYDRAPHTAL 8055 (1:5 emulsified), based on the pelt weight

vegetable tannage: 0,5 - 2,0 % HYDRAPHTAL 8055 (1:5 emulsified), based on the pelt weight

STORAGE HINT:

Protect from cold.

Die vorstehenden Angaben sollen lediglich Hinweise und Anregungen geben, ohne rechtsverbindlichen Charakter zu haben. Sie bedeuten insbesondere nicht, bestimmte Eigenschaften der Produkte oder deren Eignung für einen bestimmten Zweck zuzusichern. Unsere Kunden müssen eigenverantwortlich unsere Produkte auf ihre Eignung für die vorgesehenen Verfahren und Zwecke prüfen, ggfs. durch Herstellen von Proben und Durchführen von Versuchen. Etwa bestehende gewerbliche Schutzrechte sind zu beachten. Im übrigen gelten unsere Allgemeinen Geschäftsbedingungen.

As informações acima dispostas tratam-se de observações e sugestões sem qualquer caráter juridicamente vinculante. Em particular, as informações não têm como objetivo garantir quaisquer propriedades dos produtos ou a adequação de sua aplicação para finalidades determinadas. Reforçamos que é de responsabilidade de nossos clientes avaliar os nossos produtos em relação à adequação de sua aplicação para os métodos e propósitos previstos, certificando-se da adequação, em caso de quaisquer dúvidas, por meio de amostras e testes. Devem ser observados quaisquer direitos de propriedade industrial.

Além disso, aplicam-se nossos Termos e Condições Gerais.

These particulars only provide information and suggestions, without being legally binding. They do not in any way guarantee certain properties of the products nor their suitability for a specific purpose. It is the customer's own responsibility to test our products with regard to their suitability for the intended purposes and process, by preparing samples and carrying out tests. Attention must also be paid to any existing industrial rights. Besides this, our "General Terms of Business" apply.